



BUREAU
VERITAS

Test Report: (8722)085-0202

Received Date: July 26, 2022
Report Date: July 30, 2022

PASS

SUBMITTER

CONTEMPORARY LEATHERS PVT LTD
2/400, MOUNT POONAMALLEE HIGH ROAD, IYYANPANTHANGAL,
POONAMALLEE, CHENNAI – 600 056.



STYLE NUMBER	WRN004,WRN007.
PRODUCT DESCRIPTION	CLARA TURNLOCK SATCHEL,LILY TOTE BAG – LEATHER SWATCH
EXECUTIVE SUMMARY	Overall Rating = PASS, The sample(s) MEET all the tested requirement(s).
REMARKS	ULR-TC609222000019369F

TECHNICAL QUESTIONS

Sugumar P
Directline +91-40701600. Ext:641
sugumar.p@bureauveritas.com

SIGNATURES

Bureau Veritas Consumer Products Services (I) Pvt Ltd.

Sugumar.P
Lab Manager
Analytical Department

GENERAL INFORMATION

Jagadish V.P
Directline +91-40701600. Ext:672
Jagadish.vp@bureauveritas.com

C/N: (8722)085-0200 SS/RP

Certificate No. TC-6092 (Pls Refer the website www.nabl-inida.org to view the scope of accreditation)

Bureau Veritas Consumer Products Services (I) Pvt. Ltd.
AKR Tech Park, Ground floor,
C Block, Survey no 112,
BANGALORE
Tel: 0091-80-40701600 Fax: 0091-80-40701655

This report is governed by, and incorporates by reference, CPS Conditions of Service as posted at the date of issuance of this report at <http://www.bureauveritas.com/home/about-us/our-business/cps/about-us/terms-conditions/> and is intended for your exclusive use. Any copying or replication of this report to or for any other person or entity, or use of our name or trademark, is permitted only with our prior written permission. This report sets forth our findings solely with respect to the test samples identified herein. The results set forth in this report are not indicative or representative of the quality or characteristics of the lot from which a test sample was taken or any similar or identical product unless specifically and expressly noted. Our report includes all of the tests requested by you and the results thereof based upon the information that you provided to us. Measurement uncertainty is only provided upon request for accredited tests. You have 60 days from date of issuance of this report to notify us of any material error or omission caused by our negligence or if you require measurement uncertainty; provided, however, that such notice shall be in writing and shall specifically address the issue you wish to raise. A failure to raise such issue within the period shall constitute your unqualified acceptance of the completeness of this report, the tests conducted and the correctness of the report contents.



**BUREAU
VERITAS**

Test Report: (8722)085-0202

Received Date: July 26, 2022
Report Date: July 30, 2022

SEASON	AW22
COLORS SUBMITTED	Brown
FINISHES (IF APPLICABLE)	/
COUNTRY OF ORIGIN	INDIA
SIZE SUBMITTED	A4 SIZE – 4 NO EACH
FABRIC WEIGHT	/
FABRIC COUNT	/
COUNTRY OF DESTINATION	EU (UK)
SUBMITTED FIBER CONTENT	Ashbourne- Cow Oily Pull Up
ACTUAL FIBER CONTENT	/
SUGGESTED FIBER CONTENT	/
PROTOCOL NUMBER	/
PROTOCOL STAR LEVEL	/
FAIL RETEST	/
PREVIOUS REPORT NUMBER	/
RETEST SAMPLE NUMBER	/
REPORT EXPIRATION DATE	/



**BUREAU
VERITAS**

Test Report: (8722)085-0202

Received Date: July 26, 2022
Report Date: July 30, 2022

TEST NAME	OVERALL RATINGS
AZO DYES	PASS
FORMALDEHYDE	PASS
ALKYLPHENOL (AP)	PASS
ALKYLPHENOL ETHOXYLATES (APEO)	PASS
PH VALUE	PASS
CHROMIUM VI (AGING)	PASS



Test Report: (8722)085-0202

Received Date: July 26, 2022
Report Date: July 30, 2022

TESTED PROPERTY	REQUIREMENTS	RESULTS	RATING
Azo dyes and related salts EC No. 1907/2006 annex XVII and its amendments item no. 43 / EN ISO 14362-1:2017 / ISO 17234-1:2020	Textile & Leather : maximum: 30 mg/kg	Meet	PASS

Test Item(s)	Test Item or Component Description(s)
I001	BROWN COW OILY PULL UP

Test Item(s)	Test Method(s)	Result(s) [Unit in mg/kg]		Conclusion
		Detected Analyte(s)	Concentration	
I001	II	Not detected	Not detected	Pass

Key(s) :

For textile and other materials [Test Method I] :

European Standard EN ISO 14362-1: 2017

For leather materials [Test Method II] :

International Standard ISO 17234-1: 2015

Detection Limit (mg/kg) - Each of the listed azo dyes in test list : 5

Remark(s) :

- Quantitative and qualitative determinations of aromatic amines are carried out by gas chromatography with mass spectrometer (GC-MS) while qualitative confirmation is carried out by high performance liquid chromatography with diode array detector (HPLC-DAD).

- The test list of azo dyes and arylamine salts is summarized in below table.

Test List of Azo Dyes and Arylamine Salts [Azo dyes and related salts (ISO 17234-1:2015 / EN ISO 14362-1:2017 (Mod))] :

Number	Name of Analyte(s)	CAS-Nr	Number	Name of Analyte(s)	CAS-Nr.
1	4-Aminobiphenyl	92-67-1	15	4,4'-Methylene-bis-(2-chloro-aniline)	101-14-4
2	Benzidine	92-87-5	16	4,4'-Oxydianiline	101-80-4
3	4-Chloro-o-toluidine	95-69-2	17	4,4'-Thiodianiline	139-65-1
4	2-Naphthylamine	91-59-8	18	o-Toluidine	95-53-4
5	o-Aminoazotoluene	97-56-3	19	4-Methyl-m-phenylenediamine (2,4-Tolulendiamine)	95-80-7
6	5-Nitro-o-toluidine (2-Amino-4-nitrotoluene)	99-55-8	20	2,4,5-Trimethylaniline	137-17-7
7	4-Chloroaniline (p-Chloroaniline)	106-47-8	21	o-Anisidine	90-04-0
8	4-Methoxy-m-phenylenediamine (2,4-Diaminoanisole)	615-05-4	22	4-Aminoazobenzene	60-09-3
9	4,4'-Methylenedianiline (4,4'-Diaminodiphenylmethane)	101-77-9	23	2,4-Xylidine	95-68-1
10	3,3'-Dichlorobenzidine	91-94-1	24	2,6-Xylidine	87-62-7
11	3,3'-Dimethoxybenzidine	119-90-4	25	4-Chloro-o-toluidinium chloride	3165-93-3
12	3,3'-Dimethylbenzidine	119-93-7	26	2-Naphthylammoniumacetate	553-00-4
13	4,4'-Methylenedi-o-toluidine (3,3'-Dimethyl-4,4'-diaminodiphenylmethane)	838-88-0	27	4-Methoxy-m-phenylene diammonium sulphate	39156-41-7
14	p-cresidine	120-71-8	28	2,4,5-trimethylaniline hydrochloride	21436-97-5

CAS-Nr. = Chemical Abstracts Service Registry Number



BUREAU
VERITAS

Test Report: (8722)085-0202

Received Date: July 26, 2022
Report Date: July 30, 2022

TEST RESULTS FOR

TESTED PROPERTY	REQUIREMENTS	RESULTS	RATING
Alkylphenol (AP) (ISO 21084:2019 (Mod))			
	100mg/kg (total)	Meet	Pass

Test Item(s)	Item / Component Description(s)	Location(s)	Style(s)
I001	BROWN COW OILY PULL UP	--	-

Test Item(s)	Test Method(s)	Result(s) [Unit in mg/kg]		Conclusion
		Detected Analyte(s)	Concentration	
I001	I	Not Detected	Not Detected	Pass

Key(s) :

For textile and leather materials
[Test Method I] :

International Standard ISO 21084: 2019 [European Standard EN ISO 21084: 2019]

For other applicable materials
[Test Method II] :

Tetrahydrofuran (THF) extraction with sonication for 60 minutes at 70 degree Celsius and followed by gas chromatograph mass spectrometer (GC-MS) or liquid chromatograph mass spectrometer (LC-MS) analysis. [With reference to International Standard ISO 21084: 2019]

Detection Limit (mg/kg) - APs (Sum of OPs and NPs) : 10

Remark(s):

- The test list of alkylphenols (APs) is summarized in below table.

Test List of Alkylphenols (APs) [Alkylphenol (AP) (ISO 21084:2019 (Mod))] :

Number	Name of Analyte(s)	CAS-Nr.	Number	Name of Analyte(s)	CAS-Nr.
1	Octylphenols (OPs)	Various (140-66-9, 1806-26-4, 27193-28-8)	2	Nonylphenols (NPs)	Various (104-40-5, 11066-49-2, 25154-52-3, 84852-15-3)

CAS-Nr. = Chemical Abstracts Service Registry Number

Alkylphenol ethoxylates (APEO) (ISO 18218-1:2015 / ISO 18254-1:2016 (Mod))

	100mg/kg (total)	Meet	Pass
--	------------------	------	------

Test Item(s)	Item / Component Description(s)	Location(s)	Style(s)
I001	BROWN COW OILY PULL UP	--	A

Test Item(s)	Type(s)	Test Method(s)	Result(s) [Unit in mg/kg]		Conclusion
			Detected Analyte(s)	Concentration	
I001	I	II	Not Detected	Not Detected	Pass

Key(s) :

Type I - Non-recycled materials

Type II - Recycled materials

For Textile and Other Applicable Materials
(Except Leather Materials) [Test Method I] :

With reference to European Standard EN ISO 18254-1: 2016 [International Standard ISO 18254-1: 2016] and analysis by liquid chromatograph mass spectrometer (LC-MS)

For Leather Materials [Test Method II] :

With reference to European Standards EN ISO 18218-1: 2015 [International Standard ISO 18218-1: 2015] and EN ISO 18254-1: 2016 [International Standard ISO 18254-1: 2016]

Detection Limit (mg/kg) - APEOs (Sum of OPEOs and NPEOs) : 20

AFIRM RSL Reporting Limit (mg/kg) - APEOs (Sum of OPEOs and NPEOs) : 20

Remark(s):

- The test list of alkylphenol ethoxylates (APEOs) is summarized in below table.

Test List of Alkylphenol Ethoxylates (APEOs) [Alkylphenol ethoxylates (APEO) (ISO 18218-1:2015 / ISO 18254-1:2016 (Mod))] :

Number	Name of Analyte(s)	CAS-Nr.	Number	Name of Analyte(s)	CAS-Nr.
--------	--------------------	---------	--------	--------------------	---------



BUREAU
VERITAS

Test Report: (8722)085-0202

Received Date: July 26, 2022
Report Date: July 30, 2022

1	Octylphenol ethoxylates (OPEOs)	Various (9002-93-1, 9036-19-5, 68987-90-6)	2	Nonylphenol ethoxylates (NPEOs)	Various (9016-45-9, 26027-38-3, 37205-87-1, 68412-54-4, 127087-87-0)
---	---------------------------------	---	---	---------------------------------	---

CAS-Nr. = Chemical Abstracts Service Registry Number

TESTED PROPERTY	REQUIREMENTS	RESULTS	RATING
Formaldehyde (ISO 17226-1:2018)			
	Kidswear requirement: Under 36 months 16mg/kg for all other 70mg/kg	Meet	PASS

Test Item(s)	Test Item or Component Description(s)
I001	BROWN COW OILY PULL UP

Test Item(s)	Type(s)	Test Method(s)	Unit(s)	Req.	Result(s)	Conclusion
I001	--	II	mg/kg	≤ 75	Not detected	Pass

Key(s) :

For textile, paint, print, surface coating, printed or coated plastic or rubber or foam, fusing, padding, feather, down, glue, wood, paper and straw materials :

Test Method I - With reference to ISO 14184-1

For leather materials :

Test Method II - International Standard ISO 17226-1: 2018 [European Standard EN ISO 17226-2: 2019]

Detection Limit (mg/kg) - 16

pH value (ISO 3071:2006 / EN ISO 4045:2018)

	Leather and suede: 3.2 minimum	Meet	PASS
	Other materials 4.0 – 7.5		

Test Item(s)	Test Item or Component Description(s)
I001	BROWN COW OILY PULL UP

Test Parameter(s)	Unit(s)	Measurement or Reading	Result(s)	Conclusion
Test Item(s)	--	--	1001	1002
Temperature of Extracting Solution (KCl)	°C	--	21.3	21.6
pH Value of Aqueous Extract	--	--	4.5	4.2
Difference Figure	--	--	--	--



Test Report: (8722)085-0202

Received Date: July 26, 2022
Report Date: July 30, 2022

TESTED PROPERTY	REQUIREMENTS	RESULTS	RATING
Hexavalent chromium EC No. 1907/2006 Annex XVII and its amendments item no. 47 /ISO 17075-1:2017			
	<3mg/kg	Meet	PASS

Test Item(s)	Test Item or Component Description(s)
I001	BROWN COW OILY PULL UP

Test Item(s)	Unit(s)	Req.	Result(s)	Conclusion
I001	mg/kg	≤ 3	Not detected	Pass

Key(s) :

Test Method (Natural Leather Materials) :	- International Standard ISO 17075-1: 2017 with The condition of aging method for Test Method was 80 ± 2 degree Celsius (°C) for 24 hours with relative humidity of less than 5 %.
---	--

Detection Limit (mg/kg) :3

Remark(s) :
-

---END OF REPORT---